

MEDITERRANEA

scheda tecnica

CARATTERISTICHE		UNITÀ	VALORI		METODO DI PROVA
PESO TOTALE		g/m ²	±10%	900	UNI EN ISO 2286 parte 2
SPESSORE		mm	±0,10	1,00	UNI EN ISO 2286 parte 3
RESISTENZA ALLA TRAZIONE	ordito	N/5 cm	≥	300	UNI EN ISO 1421 metodo 1
	trama			150	
ALLUNGAMENTO PERCENTUALE A ROTTURA	ordito	%	≥	5%	UNI EN ISO 1421 metodo 1
	trama			5%	
ALLUNGAMENTO PERCENTUALE SOTTO CARICO	ordito	%	≤	2%	UNI 4818 part 7° under a load of 100 N
	trama			2%	
RESISTENZA ALLA LACERAZIONE A SECCO (PANTALONE)	ordito	N	≥	10	UNI EN ISO 4674-1 metodo B
	trama			10	
RESISTENZA AL DISTACCO DEL RIVESTIMENTO DAL SUPPORTO		N/5 cm	≥	40	UNI EN ISO 2411
RESISTENZA ALLE FLESSIONI RIPETUTE (METODO BALLY)		cicli	≥	100000	UNI EN ISO 7854
ALLA LUCE ARTIFICIALE (XENO TEST)		scala dei blu	≥	6	UNI EN ISO 105-B02
Composizione 70% PVC; 15% COT; 15% P ORGANIC			Ultimo aggiornamento: 16-04-2024		

MEDITERRANEA

data sheet

CHARACTERISTICS		UNIT	VALUE		TEST METHOD
TOTAL WEIGHT		g/m ²	±10%	900	UNI EN ISO 2286 parte 2
THICKNESS		mm	±0,10	1,00	UNI EN ISO 2286 parte 3
TENSILE STRENGTH	warp	N/5 cm	≥	300	UNI EN ISO 1421 metodo 1
	weft			150	
ELONGATION AT BREAK	warp	%	≥	5%	UNI EN ISO 1421 metodo 1
	weft			5%	
PERCENTAGE ELONGATION UNDER LOAD	warp	%	≥	2%	UNI 4818 part 7° under a load of 100 N
	weft			2%	
TEAR RESISTANCE (TROUSER)	warp	N	≥	10	UNI EN ISO 4674-1 metodo B
	weft			10	
DETERMINATION OF COATING ADHESION		N/5 cm	≥	40	UNI EN ISO 2411
RESISTENCE TO DAMAGE BY FLEXING (BALLY METHOD)		cycles	≥	100000	UNI EN ISO 7854
COLOUR FASTNESS TO ARTIFICIAL LIGHT		Blue wool scale	≥	6	UNI EN ISO 105-B02
Composition: 70% PVC; 15% COT; 15% P ORGANIC			Last update: 16-04-2024		